

8W5

Off-White Surfacer

Technical Data Sheet

Product Group

Primer Surfacer

Characteristics



Product
Information

- A two-component polyurethane primer surfacer providing excellent filling properties.
- May be applied to aerospace aluminum and composite substrates to fill and smooth surface irregularities in combination with AkzoNobel Aerospace Coatings specification primers, conductive coatings and topcoats.

Components



Curing Solution
Thinner

Curing Solution: 50C3
Thinner: 66C20 or 66C28

Specifications



Qualified
Product List

Boeing	BAC 5837 (Note: BAC 5837 - use as pinhole filler only)
EADS (CASA)	Z12.216
Hamilton Sundstrand	HS7136, Type I, Class A
Lear Fan Corp, (US)	LMS 5002A
Northrop Grumman	GC130CS1
Pratt & Whitney	PWA36014

For most recent up-date or missing specifications please check the qualified product list (QPL) on www.akzonobel.com/aerospace

Surface Conditions



Cleaning

Surface pretreatment is an essential part of the painting process.

- **Aluminum:** Follow specification requirements for pretreatment and primer application.
- Apply 8W5 surfacer to fill surface irregularities prior to the subsequent steps in the coating process.
- **Laminates:** Clean thoroughly with non-residual solvent.
- Fill laminate "pinholes" with Static Conditioner Filler 28C1 in accordance with directions, before applying 8W5 surfacer.

8W5 Off-White Surfacer

Instruction for Use



Mixing Ratio
(volume)

4 parts
1 part
2 parts

Base 8W5
Curing Solution 50C3
Thinner 66C20 or 66C28 for spray
consistency. Do not exceed 3 parts thinner
maximum by volume.

- Stir or Shake until all pigment is uniformly dispersed before adding curing solution.
- Stir the catalyzed mixture thoroughly.



Induction Time

15 minutes.



Initial Spraying
Viscosity
(25°C/77°F)

60 – 74 seconds ISO-Cup 4
24 – 34 seconds Signature Zahn-Cup #2
25 – 35 seconds Ford Cup #4



Note

Viscosity measurements are provided as guidelines only and are not to be used as quality control parameters. Certified information is provided by certification documentation available on request.



Pot life
(25°C/77°F)

6 hours.



Dry Film
Thickness
(DFT)

As required

8W5 Off-White Surfacer

Application Recommendations



Conditions

Temperature: 15 – 35°C
59 – 95°F
Relative Humidity: 35 – 75%



Note

The quality of the application of all coatings will be influenced by the spray equipment chosen and the temperature, humidity, and air flow of the paint application area. When applying the product for the first time, it is recommended that test panels be prepared in order to identify the best equipment settings to be used in optimizing the performance and appearance of the coating.



Equipment

Air 1.8 mm nozzle orifice
HVLP 1.4 mm nozzle orifice
Air Assisted, Electrostatic .33 mm nozzle orifice



Number of
Coats

Spray on one or more coats as required for adequate filling of imperfections in substrate. Allow final coat to stand 4-6 hours, sand with fine paper, then topcoat with selected AkzoNobel Aerospace Coatings topcoat.










Cleaning of
Equipment

MEK, C28/15

8W5 Off-White Surfacer

Physical Properties

	Drying Times (25 +/- 2°C / 77 +/- 2°F, 55 +/- 5% RH)	Minimum topcoat re-coat time 6 – 8 hours (depending on film thickness) prior to sanding and application of topcoat.								
	Theoretical Coverage	14.5m ² per liter ready to apply at 25 µm dry film thickness 592 ft ² per US gallon ready to apply at 1 mil dry film thickness								
	Dry Film Weight	52.44 g/m ² at 25.4 micron .0107 lbs/ft ² at 1 mil								
	Volatile Organic Compounds	Max 570 g/l Max 4.8 lb/gal, reduced with 2 parts 66C20 thinner, per ASTM D3960								
	Gloss (60°)	Flat								
	Color	Off-White								
Conductivity	Non-conductive									
	Flash-point	<table border="0"> <tr> <td>8W5</td> <td>26°C (78°F)</td> </tr> <tr> <td>50C3</td> <td>28°C (82°F)</td> </tr> <tr> <td>66C20</td> <td>-5°C (23°F)</td> </tr> <tr> <td>66C28</td> <td>15°C (59°F)</td> </tr> </table>	8W5	26°C (78°F)	50C3	28°C (82°F)	66C20	-5°C (23°F)	66C28	15°C (59°F)
8W5	26°C (78°F)									
50C3	28°C (82°F)									
66C20	-5°C (23°F)									
66C28	15°C (59°F)									

8W5 Off-White Surfacer



Storage

Store the product dry and at a temperature between 5 and 38°C / 40 and 100°F per AkzoNobel Aerospace Coatings specification. Store in the original unopened containers. Storage temperature may vary per OEM specification requirements. Refer to container label for specific storage life information.

Shelf life
5 - 38°C
(40 - 100°F)

18 months per AkzoNobel Aerospace Coatings commercial specification. For 8W5 and 50C3. 24 months for 66C20 and 66C28. Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Safety Precautions

Comply with all local safety, disposal and transportation regulations. Check the Material Safety Data Sheet (MSDS) and label of the individual products carefully before using the products. The MSDS's are available on request.

Issue date: January 2015 (supersedes May 2013) - FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given is subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.